

## Renewable Lubricants, Inc.

Distributed By: DM's Bio-Based Fluid Supply Inc. 10 McEwan Dr. W, Unit 4B Bolton, ON, Canada L7E 1H1

Voice: 905.951.1100 Fax: 905.951.2100 www.dmsbiobased.ca

## Bio-STX<sup>TM</sup> Hydraulic Fluid (ISO 68)



## "Bio-based Lubricants that Perform Like Synthetics"

Bio-STX<sup>TM</sup> Hydraulic Fluid ISO 68 is an ultimately biodegradable vegetable based formula that meets and exceeds Vickers M-2950-S, Vickers 1-286-5, U.S. Steel 126, and U.S. Steel 127. Bio-STX<sup>TM</sup> Hydraulic Fluid 68 is formulated to perform in industrial hydraulic systems that require Anti-Wear (AW), anti-rust, anti-oxidation, anti-foam, and demulsibility properties. The anti-wear performance meets the requirements for Vickers 35VQ-25 and V-104C (ASTM D-2882) vane pump stand tests, and DIN 51524 Part 2 load stage 10.

Bio- STX™ Hydraulic Fluids 68 is highly inhibited against moisture and rusting in both fresh and sea water and pass both A and B Sequences of the ASTM D-665 Turbine Oil Rust Test. Incorporating the super high viscosity index of the Stabilized\* High Oleic Base Stocks (HOBS) into the formula, increases the viscosity index past synthetic levels (Energy Conserving Formulas). Zinc-free additive systems have also been developed that are environmentally friendly and meet or exceed pump requirements.

The super high viscosity index of the HOBS naturally improves the thermal shear stability of the formula and increases load capacity. The HOBS's extremely low volatility increases the flash and fire safety features in the formula. It is formulated to provide seal conditioning for longer seal life and to reduce oil leakage from the system. Bio-Hydraulic Fluids should be used in hydraulic systems where low toxicity and BIODEGRADABILITY properties are required. Bio-STX™ Hydraulic Fluid is an ENVIRONMENTALLY RESPONSIBLE lubricant that is formulated from renewable agricultural plant resources. We believe Earth's environmental future rests in the use of renewable materials.

STABILIZED by Renewable Lubricants<sup>TM</sup>\* is RLI's trademark on their proprietary and patented anti-oxidant, anti-wear, and cold flow technology. High Oleic Base Stock (HOBS) are agricultural vegetable oils. This Stabilized technology allows the HOBS to perform as a high performance formula in high and low temperature applications, reducing oil thickening and deposits.

Patented Product: US Patent 6,383,992, US Patent 6,534,454 with additional Pending and Foreign Patents \* Trademark of Renewable Lubricants \* Inc. Copyright 1999 Renewable Lubricants \* Inc.

Availability F.O.B.: Bolton, ON, Canada 5 Gallon Pails Drums Bulk

<sup>&</sup>lt;sup>1</sup> Ultimate Biodegradation (Pw1) within 28 days in ASTM D-5864 Aerobic Aquatic Biodegradation of Lubricants

## Bio-STX<sup>TM</sup> Hydraulic Fluids ISO 68

			Spec.
TYPICAL SPECIFICATIONS Page 2	METHOD	ISO 68	Requirements
Specific Gravity @ 15.6°C	ASTM D-287	.90	Report
Viscosity @ 40°C	ASTM D-445	66.16	Note 1
Viscosity @ 100°C	ASTM D-445	12.2	Note 1
Viscosity Index	ASTM D-2270	191	90 (min)
	113111111111111111111111111111111111111	191	) (IIII)
Pour Point	ASTM D-97	-20°C	Note
Flash Point (COC)	ASTM D-92	280°C	198°C (min
Fire Point (COC)	ASTM D-92	310°C	218°C (min
Foam Sequence I, II, III (10 min)	ASTM D-892	0 Foam	0 Foan
Rust Prevention	ASTM D-665		
Distilled Water	7151111 2 003	Pass	Pas
Syn. Sea Water		Pass	Pas
Copper Corrosion Strip 3hr @ 100°C	ASTM D-130	1B	DIN 51524 2(max
Rotary Bomb Oxidation, (minutes)	ASTM D-2272	165	USS 120 (min
Neutralization Number mg KOH/g	ASTM D-974	0.25	1.5 (max
Swell of Synthetic NBR-L Rubber, % (Avg.) Volume Change (%) Shore A Hardness Change (%)	DIN 53538, Part 1	5.0 -4	0 to 1: 0 to -
Demulsibility, ML Oil/Water/Emulsion	ASTM D-1401	40/40/0	40 (max (30 minutes
4-Ball Wear, 1h, 167°F, 1200 RPM, 40 kg	ASTM D-4172	0.46	USS 127 0.5 (max
FZG Test	DIN 51354	10	US.Steel 10 (min
<b>Biodegradation Classification</b>	ASTM D-5864	Ultimate PW1	Ultimate PW
<b>Environmentally Friendly</b>	ISO 15380	yes	
USDA Biobased Tested	New Carbon	yes	meets/exceeds
	1.0W Carbon		over 50%
Note 1 Viscosity Sufficient for Application Note 2 Not Required			Over 50%